

To be completed and sent to: _____



PROVISIONAL TECHNICAL SPECIFICATION



SUPPLIER		ARTICLE
Name :	Aydin Örne Sanayi Ve Ticaret A.S.	Supplier Reference : DT AYLI 150 51 00101
Address :	Saray Mah. Naya Sk, No:3 34768 - Ümraniye ISTANBUL - TURKEY	Customer's Reference:
Tel :	+90 216 633 2424	Exclusivity : YES / NO
Fax :	+90 216 633 2431	

YARN DETAILS			
Material	%		
PES	92		
ELASTANE -Lycra	8		

PROVISIONAL PHYSICAL CHARACTERISTICS			
Parameter	Technical Specification	Sample Test Results	Test Method
Width (cm) :	150 cm +/-%3 (145 cm-155 cm)		
Weight (g/m ² or g/m) :	100 g/m ² +/- 10% (90 g/m ² - 110 g/m ²)		
Shrinkage Warp (%) :	+/- 5%		
Shrinkage Weft (%) :	+/- 5%		
Skewness (%) :	max 5%		

Elongation / Modulus		Effective Weight = 3,6 kg	N° of Cycles = 2
Elongation Warp (%) :		RIGID	P14 EXTENSION
Elongation Weft (%) :		105 +/- %15	P14 EXTENSION

Modulus		Measured on 2nd Outgoing Curve	Cycling Load= 3,6 kg
Warp @ %		RIGID	P14 EXTENSION
Weft @ %		100 +/- %30	P14 EXTENSION
Pattern Repeat Length :	-		
Pattern Repeat Width :	-		

PROVISIONAL COLOR FASTNESS			
TEST	Color Change	Stainig	Test Method
Colour fastness to washing	min 4	min 3/4	ISO 105 C06 B1S
Colour fastness to water	min 4	min 3/4	ISO 105 E01
Colour fastness to perspiration	min 4	min 3/4	ISO 105 E04
Colour fastness to perspiration	min 4	min 3/4	ISO 105 E04
Colour Fastness to Sea Water	min 4	min 3/4	ISO 105 E02
Colour Fast to Chlorinated Water	min 3/4		ISO 105 E03
Colour fast. to rubbing-Wet/dry	min 3/4		ISO 105 X12
Phenolic Yellowing	min 4/5		M&S C20 for White and pale shades
Light fastness	For turquoise 2, neon shades 1/2-other shades ≥3/4		ISO 105 B02
pH	4,5-7		

CARE SYMBOLS									

30°C sensitive washing, don't bleaching, Ironing at low temperature, Dry cleaning

OTHER INFORMATION	
Oeko-Tex	02.T.2346
Process Route	Knitting/Washing/Pre-SettingDyeing/Final Setting/Quality Control
Machine Type	