

To be completed and sent to: _____



PROVISIONAL TECHNICAL SPECIFICATION



SUPPLIER	
Name :	Aydin Orme Sanayi Ve Ticaret A.S.
Address :	Saray Mah. Naya Sk, No:3 34768 - Ümraniye ISTANBUL - TURKEY
Tel :	+90 216 633 2424
Fax :	+90 216 633 2431

ARTICLE	
Supplier Reference :	JD U31165 150 090 U1
Customer's Reference:	
Exclusivity :	YES / NO

YARN DETAILS			
Material	%		
RCY PES	93		
ELASTAN	7		

PHYSICAL CHARACTERISTICS			
Parameter	Technical Specification	Sample Test Results	Test Method
Width (cm) :	150 cm \pm 3% (145 cm-155 cm)		
Weight (g/m ² or g/m) :	90 g/m ² \pm 10% (81 g/m ² - 99 g/m ²)		
Shrinkage Warp (%) :	\pm 5%		
Shrinkage Weft (%) :	\pm 5%		
Skewness (%) :	max 5%		

Elongation / Modulus		Effective Weight = 3,6 kg	N° of Cycles = 2
Elongation Warp (%) :		85 \pm 15	P14 EXTENSION
Elongation Weft (%) :		104 \pm 15	P14 EXTENSION

Modulus		Measured on 2nd Outgoing Curve	Cycling Load= 3,6 kg
Warp @ %		250 \pm 30	P14 EXTENSION
Weft @ %		87 \pm 30	P14 EXTENSION
Pattern Repeat Length :	-		
Pattern Repeat Width :	-		
pH		4,5-7	

PROVISIONAL COLOR FASTNESS			
TEST	Color Change	Stainig	Test Method
Colour fastness to washing	min 4	min 3/4	ISO 105 C06 B1S
Colour fastness to water	min 4	min 3/4	ISO 105 E01
Colour fastness to perspiration	min 4	min 3/4	ISO 105 E04
Colour fastness to perspiration	min 4	min 3/4	ISO 105 E04
Colour Fastness to Sea Water	min 4	min 3/4	ISO 105 E02
Colour Fast to Chlorinated Water		min 3/4	ISO 105 E03
Colour fast. to rubbing-Wet/dry		min 3/4	ISO 105 X12
Phenolic Yellowing		min 4/5	M&S C20 for White and pale shades
Light fastness	For turquoise 2, neon shades 1/2-other shades \geq 3/4		ISO 105 B02

CARE SYMBOLS									

30°C sensitive washing, don't bleaching, Ironing at low temperature, Dry cleaning

OTHER INFORMATION	
Oeko-Tex	02.T.2346
Process Route	Knitting/Washing/Pre-SettingDyeing/Final Setting/Quality Control
Machine Type	