

To be completed and sent to: _____



PROVISIONAL TECHNICAL SPECIFICATION



SUPPLIER	
Name :	Aydin Orme Sanayi Ve Ticaret A.S.
Address :	Saray Mah. Naya Sk, No:3 34768 - Ümraniye ISTANBUL - TURKEY
Tel :	+90 216 633 2424
Fax :	+90 216 633 2431

ARTICLE	
Supplier Reference :	JD 030107 150 230 01 00
Customer's Reference:	
Exclusivity :	YES / NO

YARN DETAILS			
Material	%		
PA 6	91		
ELASTANE	9		

PHYSICAL CHARACTERISTICS			
Parameter	Technical Specification	Sample Test Results	Test Method
Width (cm) :	150 cm -/+ %3 (145 cm-155 cm)		
Weight (g/m ² or g/m) :	230 g/m ² -/+ 5% (218 g/m ² - 241 g/m ²)		
Shrinkage Warp (%) :	+/- 5%		
Shrinkage Weft (%) :	+/- 5%		
Skewness (%) :	max +/- 5%		

Elongation / Modulus		Effective Weight = 3,6 kg	N° of Cycles = 2
Elongation Warp (%) :		138 +/- %15	P14 EXTENSION
Elongation Weft (%) :		36 +/- %15	P14 EXTENSION

Modulus		Measured on 2nd Outgoing Curve	Cycling Load= 3,6 kg
Warp @	%	215 +/- %30	P14 EXTENSION
Weft @	%	2500 +/- %30	P14 EXTENSION
Pattern Repeat Length :	-		
Pattern Repeat Width :	-		
Colour fast. to rubbing-Wet/dry		min 3/4	ISO 105 X12
Phenolic Yellowing		min 4/5	M&S C20 for White and pale shades
Light fastness		For turquoise 2, neon shades 1/2-other shades ≥3/4	ISO 105 B02

CARE SYMBOLS									
30°C sensitive washing, don't bleaching, Ironing at low temperature, Dry cleaning									

OTHER INFORMATION	
Oeko-Tex	02.T.2346
Process Route	Knitting/Washing/Pre-Setting/Dyeing/Final Setting/Quality Control
Machine Type	