



To be completed and sent to: _____

**PROVISIONAL TECHNICAL SPECIFICATION****SUPPLIER**

Name : Aydin Örne Sanayi Ve Ticaret A.S.
Address : Baglar Mah. Yalcin Kores Cad. No:20
 Erdinc Binalari B Blok Kat:5
 34212 GUNESLI, ISTANBUL, TURKEY
Tel : +90 850 723 65 75
Fax :

ARTICLE

Supplier Reference : JD 050309 155 210 01
Customer's Reference:
Exclusivity : YES / NO

YARN DETAILS / COMPOSITION

POLYAMIDE (PA)	79%	
ELASTANE (EA)	21%	
	±3 Tolerance	

STANDARD 100
02.T.2346STANDARD 100
22.HTR.03657STeP
22002949**PROVISIONAL PHYSICAL CHARACTERISTICS**

PARAMETERS	TECHNICAL SPECIFICATIONS	TOLERANCE	TEST METHOD
Width (cm)	155 ±5%	147,3 cm - 162,8 cm	
Weight (g/m²)	210 ±5%	199,5 g/m² - 220,5 g/m²	ISO 3801
Weight (g/m)	325,5 ±5%	309,2 g/m - 341,8 g/m	
Dimensional Stability Warp (%)	±5		ISO 6330 - ISO 3759 ISO 5073
Dimensional Stability Weft (%)	±5		
Pattern Repeat Length	-		
Pilling	≥ 3/4		ISO 12945-1 @7200
Pilling	≥ 3/4		ISO 12945-2 @2000
Snagging	≥ 2/3		BS 8479 @2000
Air Permability (cm³/s/cm²)	287		ISO 9237
Wrinkle Recovery (Original)	3/4		ISO 9867
pH	4,0 - 7,5		ISO 3071

Elongation

Effective Weight = 7N

N° of Cycles = 5

Elongation Warp (%)	180 ±15%	153% - 207%	ISO 20932-1/A
Elongation Weft (%)	150 ±15%	20% - 50%	ISO 20932-1/A

Modulus

Measured on 5th Outgoing Curve

Cycling Load = 7N

Warp @40% (cN)	150 ±40%	127,5 cN - 172,5 cN	ISO 20932-1/A
Weft @40% (cN)	65 ±40	25 cN - 105 cN	ISO 20932-1/A

Residual Elongation/Growth

After 1 min

Warp (%)		≤ 15	ISO 20932-1/A
Weft (%)		≤ 15	ISO 20932-1/A

PROVISIONAL COLOR FASTNESS

TEST	COLOR CHANGE	STAINING	TEST METHOD
*CF to Washing	min 4	min 3/4	ISO 105 C06 A1S
*CF to Water	min 4	min 3/4	ISO 105 E01
*CF to Perspiration - Acid	min 4	min 3/4	ISO 105 E04
*CF to Perspiration - Alkaline	min 4	min 3/4	ISO 105 E04
*CF to Sea Water	min 4	min 3/4	ISO 105 E02
*CF to Chlorinated Water @ 20ppm	min 3/4	-	ISO 105 E03
*CF to rubbing - Wet/Dry	-	min 3/4	ISO 105 X12
CF to Phenolic Yellowing	min 4/5		ISO105 X18
*CF to Artificial Light	For turquoise 2, neon shades 1/2-other shades ≥3/4		ISO 105 B02

CARE SYMBOLS

--	--	--	--	--	--	--	--	--

30°C sensitive washing, Don't bleaching, Ironing at low temperature, Dry cleaning short cycle, Don't tumble dry

OTHER INFORMATION

Process Route	Knitting/Washing/Pre-Setting/Dyeing/Final Setting/Quality Control
Machine Type	

*Colour fastness value is vary depending on the recipe and dye group in which the fabrics is dyed. The values written above are standard values. Fastness values specified in lab dip will be valid.